

PRODUCT DESCRIPTION

Stonclad GR is an environmentally friendly four-component, troweled, epoxy mortar system utilizing recycled materials and rapidly renewable soy based components. The system utilizes 25% recycled glass blended with an epoxy resin, amine curing agent and soy based additives. Stonclad GR can be applied at thickness ranging from 3mm to 6mm depending on application requirements. Stonclad GR cures to an extremely hard, impact resistant surface which exhibits excellent abrasion, wear and chemical resistance.

SYSTEM OPTIONS

Coatings

To improve cleanability and increase the resistance to damage from abrasion and chemical spillages, the following coatings are recommended: Stonkote GS4, Stonkote HT4.

Waterproofing

Where the total system must be waterproof, use of Stonhard's Stonproof ME7 membrane system is required, with strict adherence to application instructions.

Cove Base

To provide for an integral seal at the joint between the floor and the wall, cove bases in heights from 5 to 15 cm may be specified.

Fiberglass Reinforcement

To provide additional surface strength to the system, a surface veil of fiberglass reinforcement should be installed for areas exposed to instantaneous temperature changes of greater than 38°C.

PACKAGING

Stonclad GR is packaged in units for easy handling. Each unit consists of:

- 2 cartons, each containing:
 - 6 foil bags of Amine
 - 6 poly bags of Resin
- 12 individual bags of aggregate

Pigment

- 1 carton, containing:
 - 12 bags of part C-2 pigment

COVERAGE

Each unit of Stonclad GR will cover approximately 18.6 m² of surface at a nominal 6 mm thickness.

STORAGE CONDITIONS

Store all components of Stonclad GR between 16 to 30°C in a dry area. Avoid excessive heat and do not freeze. The shelf life is 3 years in the original, unopened container.

COLOR

Stonclad GR is available in 12 standard colors. Refer to the Stonclad Color Sheet.

SUBSTRATE

Stonclad GR, with the appropriate primer, is suitable for application over concrete, wood, brick, quarry tile, metal or Stonhard Stonset grouts. For questions regarding other possible substrates or an appropriate primer, contact your local Stonhard representative or Technical Service.

USGBC LEED RATING

Stonclad GR meets the requirements of LEED;

- MR Credit 1 – Building Reuse
- MR Credit 2 – Construction Waste Management
- MR Credit 4 – Recycled Content
- MR Credit 6 – Rapidly Renewable Materials
- IEQ Credit 4 – Low Emitting Materials
- VOC content of the total system <100 g/l

SUBSTRATE PREPARATION

Proper preparation is critical to ensure an adequate bond and system performance. The substrate must be dry and properly prepared utilizing mechanical methods. Questions regarding substrate preparation should be directed to your local Stonhard representative or Technical Service.

PHYSICAL CHARACTERISTICS

Compressive Strength.....	69 N/mm ²
(ASTM C-579)	after 7 days
Tensile Strength	12 N/mm ²
(ASTM C-307)	
Flexural Strength	28 N/mm ²
(ASTM C-580)	
Flexural Modulus of Elasticity	1.38 x 10 ⁴ N/mm ²
(ASTM C-580)	
Hardness.....	85 to 90
(ASTM D-2240, Shore D)	
Impact Resistance	>18 Nm
(ASTM D-2794)	
Abrasion Resistance	0.1 gm max. weight loss*
(ASTM D-4060, CS-17)	
Flammability	Class I
(ASTM E-648)	
Thermal Coefficient of Linear Expansion	
.....	1.5 x 10 ² mm/m°C
(ASTM C-531)	
Water Absorption.....	0.2%
(ASTM C-413)	
Cure Rate.....	24 hours for normal operations
(at 75°F/25°C)	
VOC Content	<5 g/L
(ASTM D-2369)	

*Test samples finished with one coat of high solids epoxy coating

Note: The above physical properties were measured in accordance with the referenced standards. Samples of the actual floor system, including binder and filler, were used as test specimens. All sample preparation and testing is conducted in a laboratory environment, values obtained on field applied materials may vary and certain test methods can only be conducted on lab made test coupons.

PRIMING

The use of Standard Primer is necessary for all applications of Stonclad GR over all substrates except Stonset grouts. Over Stonset grouts, Stonhard's Stonset Primer is used. Please see the appropriate primer Product Data sheet for details.

MIXING

- Proper mixing is critical for the product to exhibit the proper application properties, cure properties and ultimate physical properties.
- Mechanical mixing using a JB Blender (or equivalent c.a. 20 liter. Pail mixer) or a larger mortar mixer (e.g., a Baugh 3 Batch Mixer) is required.
- See Stonclad GR Directions for further details.

APPLYING


- DO NOT attempt to install material if the temperature of Stonclad GR components and substrate are not within 16 to 30°C. The cure time and application properties of the material are severely affected at temperatures outside of this range.
- Material must be applied immediately after mixing.
- A suitable screed applicator is used to distribute the mixed Stonclad GR onto the floor.
- Steel finishing trowels are used to compact and smooth the surface of the material to the required thickness.
- Detailed application instructions can be found in the Stonclad GR Directions.

NOTES

- Procedures for maintenance of the flooring system during operations are described in the Stonkleen Floor Cleaning Procedures Brochure.
- Specific information regarding chemical resistance is available in the Stonclad Chemical Resistance Guide.
- Safety Data Sheets for Stonclad GR are available online at www.stonhard-europe.com under Products or upon request.
- A staff of technical service engineers is available to assist with installation or to answer questions related Stonhard's flooring products.
- Requests for technical service or literature can be made through local sales representatives and offices, or corporate offices located worldwide.
- The appearance of all floor, wall and lining systems will change over time due to normal wear, abrasion, traffic and cleaning. Generally, high gloss coatings are subject to a reduction in gloss, while matte finish coatings can increase in gloss level under normal operating conditions.
- Surface texture of resinous flooring surfaces can change over time as a result of wear and surface contaminants. Surfaces should be cleaned regularly and deep cleaned periodically to ensure no contaminant build up occurs. Surfaces should be periodically inspected to ensure they are performing as expected and may require traction enhancing maintenance to ensure they continue to meet expectations for the particular area and conditions of use

CE MARKING

The harmonized European Standard EN 13813 „Screed material and floor screeds- Screed materials – “Properties and Requirements” specifies the requirements for screed materials for use in floor construction internally. Resinous flooring systems as well as resinous screeds fall under this specification they have to be CE-labeled as per Annex ZA., Table ZA.1.5 and 3.3 and fulfill the requirements of the given mandate of the Construction Products Regulation no. 305/2011


StonCor Europe Rue du Travail 9 1400 Nivelles, Belgium II
DOP-2013.01.002 EN 13813 SR-AR1.0-B2.0-IR18
Synthetic resin flooring system for use internally in buildings (system as per Product Data Sheet) Release of corrosive substances:SR Wear resistance: AR1.0 Impact Resistance: IR 18 Adhesion strength by pull off test: > B2.0 Chemical resistance:CRG*
*CRG: see Stonhard Chemical Resistance Guide

IMPORTANT:

Stonhard believes the information contained here to be true and accurate as of the date of publication. Stonhard makes no warranty, expressed or implied, based on this literature and assumes no responsibility for consequential or incidental damages in the use of the systems described, including any warranty of merchantability or fitness. Information contained here is for evaluation only. We further reserve the right to modify and change products or literature at any time and without prior notice.

Rev.9/20
© 2020 Stonhard www.stonhard.com

STONHARD®

European Offices:

Belgium	+32 674 93 710	Spain	+34 933 623 785	Germany	+49 240 541 740
France	+33 160 064 419	Portugal	+351 227 535 642	The Netherlands	+31 165 585 200
Poland	+48 422 112 768	United Kindom	+44 125 63 36 600	Italy	+39 022 53 751
		East Europe	+48 422 112 768		